

# FLUSH E/C SAMPLING KIT

(ABS019F-EC - 27mm)

This component is used when it is necessaty to sample through a suspended ceiling.

The capillary end cap fits onto the end of the pipe run. There is then a 2 meter 10mm OD nylon tube which links into the flush sampling head, which is fixed by a nylon nut/washer to the ceiling tile.

## **Installation Instructions:**


Use the correct solvent Plusbond 3019. Do not paint.

Keep pipe clean and free from dust.
Do not install in direct sunlight.
Only install with approved pipe.
Do not use solvents to clean,
only soapy water.

Part No. ABS019F-EC - 27mm

Fitting colour RED

Diameter Tolerance +/- 0.15mm



## RAW MATERIAL DATA

## Kumho ABS 750 Acrylonitrile Butaduene Styrene

**RAW MATERIAL DATA** 

OD Tol's +0.03/-0.09mm Burst Pressure 995 PSI / 68 bar

Bend Radius 40mm

NEM 10x8 -

Weight/30m 1.08kgs

OD Tol's +0.02/-0.10mm

Bend Radius 50mm

Weight/30m 0.87kgs

Temperature Range -

a guide only.

pressure values.

+130°C, Brittle point: -70°C

Technical information for use as

Pressure values given are based on

Any increase in temperature above

20°C will result in a decline in working

Products and specifications are subject

to improvements and change without

based on a 3:1 safety factor.

the short term burst pressure at 20°C

Burst Pressure 772 PSI / 53 bar

-40°C to +70°C, Occasional use up to

#### Pysica

Specific Gravity 1.04
Test Method ASTM D792

Melt Mass - Flow Rate (MFR) 200°C/21.6 kg 47 g/10 min 200°C/5.0 kg 4.1 g/10 min 220°C/10.0 kg 34 g/10 min Test Method ASTM D1238

Molding Shrinkage -Flow 0.0040 to 0.0070 in/in Test Method ASTM D955

## Mechanical:

Tensile Strength
Yield, 73°F (23°C)
1.97 in (50.0mm)
6670 psi
Test Method ASTM D638

## Tensile Elongation

Yield, 73°F (23°C) 1.97 in (50.0 mm), 15% Test Method ASTM D638

## Flexural Modulus

Yield, 73°F (23°C)
0.118 in (3.00 mm)
312000 psi
Test Method ASTM D6:

## **Flexural Strength**

Yield, 73°F (23°C) 0.118 in (3.00 mm) 9230 psi Test Method ASTM D790

## Impact

Noched Izod Impact 73°F(23°C), 0.126 in (3.20 mm), 5.5 ft·lb/ir 73°F(23°C), 0.252 in (6.40 mm), 4.8 ft·lb/ir Test Method ASTM D256

## <u>Hardne</u>

Rockwell Hardness (R-Scale) 108 Test Method ASTM D785

## **Therma**

Deflection Temperature Under Load 264 psi (1.8 MPa), Unanneald 185°F/85°C Test Method ASTM D648

Vicat Softening Temperature 203°F/95°C Test Method ASTM D1525

## <u>Flamibility</u>

Flame Rating
0.0630 in (1.60 mm) HB
0.0866 in (2.20 mm) HB
0.126 in (3.20 mm) HB
Test Method UL 94

Bisson Ltd Unit 11, Eldonwall Trading Estate, St.Phillips, Bristol, BS4 3QQ

Tel: 0117-967-9999

Fax: 0117-961-9261

http://www.abspipesandfittings.co.uk

©All rights reserved. Bisson Ltd